

STUDY CHEMICAL ADDITIVES POLYPLAST C-3 ON THE PROPERTIES OF PORTLAND CEMENT

Shakirov Tuygun Turgunjonovich

¹Tashkent Institute of Architecture and Civil Engineering (Tashkent city, Uzbekistan)

Candidate of Technical Sciences, Associate Professor

tel: +99897 733-57-44

Muminova Nilufar Abdulla Kizi

Tashkent Institute of Architecture and Civil Engineering

(Tashkent city, Uzbekistan), Basic Doctoral Student

tel: +99890 926-33-92, n.muminova94@mail.ru

ABSTRACT:

The article presents the results of research work on the development of the properties of binders with chemical additives and determines the optimal compositions.

Today, along with water, filler and binder, additives have become an indispensable component of the concrete mix. Among the many types of chemical additives, plasticizers occupy a separate place, especially the most effective of them are superplasticizers. Below are considered the most important physical and mechanical characteristics of cement kiln, which can be influenced by the introduction of additives. This will serve as a basis for understanding the behavior of cement, concrete mix and concrete obtained with the use of different types of additives, which will be devoted to the following chapters.

Key words: Chemical additives, water-cement ratio, derate cement calculation, mechanical properties of binders.

INTRODUCTION:

Water-reducing agents are additives that reduce the amount of water required to provide a concrete mix with the same fluidity as a conventional mix. These additives improve the

properties of hardening concrete and, in particular, increase its strength and durability. Usually, according to the standard, the reduction in the amount of water mixing should be at least 5%, however, technical additives-water-depleted can reduce water demand by 10-15%.

There are other reasons for using such additives, including the possibility of simultaneously lowering the content of both water and cement while maintaining the workability of the mixture and the strength of the concrete at the same level as the control portions of the mixture and concrete. Therefore, in this case, the additives additionally reduce the cement consumption. In addition, they are able to reduce the rate of heat release during cement hydration - a property that is important when concreting in hot climates or when erecting massive structures.

If these additives are introduced while maintaining the water-cement ratio, then the "workability" of the concrete mixture is improved, i.e. such additives should be considered plasticizers. This is especially important when placing concrete mix in a structure with a high coefficient of reinforcement where increased mix mobility is required.

LITERATURE REVIEW:

The degree of elaboration of the topic. Significant contributions to the study of the composition, structure and properties of QPC with mineral additives were made by: Druzhinin S.I., Kind V.A., Yung V.N., Zhuravlev V.F., Bozhenov P.I., Budnikov P.P., Glukhovskiy V.D., Butt N.M., Volzhensky A.V., Komokhov P.G., Mchedlov-Petrosyan O.P., Massatsatsa F., Kokubu M., Yamada D., Ramachandran V.S., Kalashnikov V.I.; and continue to contribute: Entin Z.B., Dvorkin L.I., Rakhimov R.Z., Khozin V.G., Ivaschenko Yu.G., Senators P.P., Palomo A., K. De Weerd, Morsy MS, Antoni V., Rossen J., Martirena F., Fernández-Jiménez A., Wang SD, Ludwig H.-M., Skibsted J. et al.

A number of scientific studies were also carried out by the scientific experts on the development of the compositions of complex-mineral additives, the improvement of the structure and properties of the cement paste. In their scientific research Kasimov E.U., Gaziev U.A., Samigov N.A., Akramov Kh.A., Mirakhmedov M.M., Makhamadaliev I.M., Tulaganov A.A., Turapov M.T., Kamilov Kh.Kh., Shakirov T.T. and others in different years have achieved certain successes and important scientific results in this direction.

MATERIALS AND METHODS:

During the research, the following materials were used:

a) binder:

Portland cement is a hydraulic binder obtained by joint grinding of cement clinker, gypsum and additives, which is dominated by calcium silicates (70-80%). This type of cement is the most widely used in all countries.

Portland cement is produced by fine grinding of clinker and gypsum. Clinker is a product of uniform firing before sintering of a homogeneous raw mixture consisting of limestone and clay of a certain composition,

which ensures the predominance of calcium silicates ($3\text{CaO} \cdot \text{SiO}_2$ and $2\text{CaO} \cdot \text{SiO}_2$ 70-80%).


Although the study of the hydration of pure cement constituents is in itself useful for tracing hydration processes in Portland cement, it cannot be directly applied to cements due to the complexity of the reactions taking place. In Portland cement, minerals do not consist of pure phases: they are solid solutions containing Al, Mg, Na, etc. The study of the hydration of alite containing different amounts of Al, Mg or Fe showed that with the same degree of hydration of Fe, alite achieves greater strength.

In this graph, you can see the chemical elements and their ratio in the composition of Portland cement in the 500 grade.

Analyzed result(FP method, Scatter)

No.	Component	Result	Unit	Stat. Err.	LLD	LLQ
1	Cl	0.0503	mass%	0.0003	0.0001	0.0004
2	Mg	0.749	mass%	0.0102	0.0144	0.0433
3	Al	1.66	mass%	0.0067	0.0071	0.0213
4	Si	9.89	mass%	0.0099	0.0007	0.0020
5	S	1.01	mass%	0.0015	0.0015	0.0046
6	K	0.769	mass%	0.0055	0.0046	0.0137
7	Ca	51.0	mass%	0.0519	0.0024	0.0072
8	Ti	0.128	mass%	0.0024	0.0036	0.0107
9	Cr	(0.0021)	mass%	0.0004	0.0012	0.0035
10	Mn	0.134	mass%	0.0021	0.0014	0.0041
11	Fe	2.59	mass%	0.0057	0.0023	0.0070
12	Cu	0.0041	mass%	0.0002	0.0004	0.0013
13	Zn	0.0030	mass%	0.0002	0.0003	0.0009
14	As	0.0013	mass%	<0.0001	0.0002	0.0006
15	Rb	0.0038	mass%	<0.0001	<0.0001	0.0003
16	Sr	0.0637	mass%	0.0003	0.0002	0.0007
17	Y	0.0040	mass%	<0.0001	0.0001	0.0003
18	Zr	0.192	mass%	0.0018	0.0007	0.0020
19	Ba	0.0255	mass%	0.0009	0.0019	0.0057
20	Pb	0.0017	mass%	0.0001	0.0003	0.0008

Spectrum



b) chemical additives:

Plasticizer C-3 has excellent plasticizing properties and effective water-reducing action.

Pastifier C-3 is applicable for light and heavy ready-mixed concrete and for the production of prefabricated structures from high-strength concrete B20 and higher, pressure reinforced concrete pipes, for the manufacture of densely reinforced structures (such as trusses, beams, columns, bridge spans), slabs and panels at stands in cassettes, on flow-aggregate and conveyor lines, in the construction of critical structures of monolithic structures with an increased degree of reinforcement and a complex configuration.

The feasibility of using a plasticizing additive is determined by the achievement of various technological indicators of efficiency in the production of reinforced concrete products and structures, the construction of structures, as well as indicators of economic efficiency during their operation.

The use of the additive allows you to achieve the following indicators:

- Increase the overall concrete mobility from P1 to P5;
- Reduce water consumption when mixed with a binder by 20 - 25%;
- Increase the strength and reliability of the final product by 25% or more (in equal-motion mixtures);
- Increase the adhesion of embedded reinforcement and metal products to concrete by 1.5 - 1.8 times;
- To obtain products with reduced moisture absorption and increased crack resistance, frost resistance (up to 350 repeated annual cycles);
- reduce the total cement consumption by up to 25%.

RESULT AND DISCUSSION:

When studying the effect of additives on the properties of cement compositions, a

factorial design of the experiment was implemented, in which the x-dosage of the additive, varying from 0 to 2%, based on the weight of cement, was taken as a significant factor. Normal density and setting time are taken as responses for the cement paste; for cement stone bending and compressive strength.

Additives were added at a concentration of 0 to 2%. Data of cement tests with the addition of PolyPlast for a period of 3.7 and 28 days.

Table 1. Influence of the chemical additive PolyPlast on the normal density cement paste.

№	Name	Control sample	Amount of chemical additives (%)				
			0,5	1,0	1,5	2,0	2,5
1	PoliPlast	0	0,5	1,0	1,5	2,0	2,5
	Amount of water (%)	27	25	24	23	22	25
	results (mm)	6,8	6,0	6,0	6,4	6,8	24,5

Table 2. Effect of the chemical additive PolyPlast on the setting time cement paste.

№	Name	Control sample	Amount of chemical additives (%)				
			0,5	1,0	1,5	2,0	2,5
1	The beginning of the setting time	65	70	85	90	100	70
2	End of setting time	340	325	310	290	280	295

Table 3 Strength characteristics of PC 500 A0 for 3 days. with addition PolyPlast C-3

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	1,28	25,6
2	500	1500	240	0,45	0,5	1,4	28
3	500	1500	240	0,43	1,0	1,55	31
4	500	1500	240	0,4	1,5	1,75	33
5	500	1500	192	0,38	2,0	1,8	33,5

Table 4 Strength characteristics of PC 500 A0 for 7 days. with addition PolyPlast C-3

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	1,8	35,9
2	500	1500	240	0,45	0,5	1,9	39,2
3	500	1500	240	0,43	1,0	2,17	43,4
4	500	1500	240	0,4	1,5	2,3	46,2
5	500	1500	192	0,38	2,0	2,35	47

Table 5 Strength characteristics of PC 500 A0 for 28 days. with addition PolyPlast C-3

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	2,6	51,2
2	500	1500	240	0,45	0,5	2,6	56
3	500	1500	240	0,43	1,0	3,1	61,9
4	500	1500	240	0,4	1,5	3,3	66
5	500	1500	192	0,38	2,0	3,35	67

1,8MPa R_{com} 33,5MPa, for 7 days R_{ban} 2,35MPa R_{com} 47MPa and for 28 days R_{ban} 3,35MPa R_{com} 67MPa. If we compare these results with the result of the control sample, we can see that, these results give up the opportunity to save cement consumption up to 25 and 30%.

Table 6 Strength characteristics of PC 500 A0 for 3 days. with addition PolyPlast C-3 when amount of cement was decreased step by step

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	1,28	25,6
2	450	1500	240	0,45	0,5	1,16	22,7
3	400	1500	240	0,43	1,0	1,22	24,2
4	360	1500	240	0,4	1,5	1,26	24,6
5	350	1500	192	0,38	2,0	1,3	25,1

Table 7 Strength characteristics of PC 500 A0 for 7 days. with addition PolyPlast C-3 when amount of cement was decreased step by step

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	1,8	35,9
2	450	1500	240	0,45	0,5	1,71	32,31
3	400	1500	240	0,43	1,0	1,73	35,1
4	360	1500	240	0,4	1,5	1,7	35,8
5	350	1500	192	0,38	2,0	1,82	36

Table 8 Strength characteristics of PC 500 A0 for 28 days. with addition PolyPlast C-3 when amount of cement was decreased step by step

№	Portland cement (gr)	Sand (gr)	Water (ml)	C/W (%)	Amount of additives (%)	Strength	
						Bend MPa	Compression MPa
1	500	1500	240	0,48	0	2,6	51,2
2	450	1500	240	0,45	0,5	2,34	45,6
3	400	1500	240	0,43	1,0	2,4	52,4
4	360	1500	240	0,4	1,5	2,44	51,9
5	350	1500	192	0,38	2,0	2,5	51,1




Figure 1. Influence of the plasticizer "PolyPlast C-3" on the properties of Portland cement

According to the data, it can be seen that the ultimate strength of 3,7 and 28 days is the highest for cement with an additive introduced in an amount of 2%, it were for 3 days R_{ban}




Figure 2. Influence of the plasticizer "PolyPlast C-3" on the properties of Portland cement

Going out these hypotheses, we have made experiments relating to the cement and achieved a good result. Experiments were held 3,7 and 28 days and the result were full expected. Results were for 3 days R_{ban} 1,3MPa R_{com} 25,1MPa, for 7 days R_{ban} 1,82MPa R_{com} 36MPa and for 28 days R_{ban} 2,5MPa R_{com} 51,1MPa.

CONCLUSION:

As a result of experiments, placificating additives made it possible to reduce water and extend the setting time. Even when the strength was determined the strength was increased due to the lowering of the water-cement ratio. In addition due to the active properties of chemical additives, we can decreased consumption of Portland cement and maintain the strength of cement stone.

REFERENCES:

1) Gaziev, U.A. Industrial waste in the production of building materials and products [Text] / U.A. Gaziev. - Tashkent: TASI, 2015 .308 p.

2) Gaziev, U.A. Industrial waste of the Republic of Uzbekistan in the production of effective building materials [Text] / U.A. Gaziev, Sh.T. Rakhimov, F.T. Kurbonov // Problems and prospects for the development of innovative cooperation in scientific research and training system: Materials of the international scientific and practical conference. - Bukhara: BukhMTI, 2017. -- S. 117-118.

3) Shakirov T.T. Studies of the phase composition and structure formation of porous aggregate// International Journal for Innovative Research in Multidisciplinary Field. ISSN: 2455-0620; Scientific Journal Impact factor: 6.497. India. Volume-5. Issue-8. Aug-2019. -P.151-155.

4) N.A. Muminova Development of properties of concretes with mineral additives. Master's dissertation work. 2019.27-33 pages.

5) Shakirov T.T. Technology of obtaining a porous aggregate from quartz porphyry and coal mining waste for light concrete / TT Shakirov. – T.: Author's abstract of the thesis of Ph.D. those. Sciences, 2010.-15-18s.

6) Gaziev U. A., Akramov X. A., Shakirov T. T., Rakhimov Sh.T. Effect of Relamix additive on cement properties// International Journal for Innovative Research in Multidisciplinary Field. ISSN: 2455-0620; Scientific Journal Impact factor: 6.497. India. Volume-5. Issue-8. Aug-2019. -P.163-165.